

PAT-NO: JP410168652A  
DOCUMENT- JP 10168652 A  
IDENTIFIER:  
TITLE: TOBACCO DEODORANT AND CRIMPED POLYOLEFIN FIBER, ITS  
PRODUCTION AND TOBACCO DEODORANT CARPET USING THE  
SAME CRIMPED FIBER  
PUBN-DATE: June 23, 1998

**INVENTOR-INFORMATION:**

NAME	COUNTRY
SHIMIZU, YOSHISHIGE	
SAKAKURA, HIDEO	
SAYAMA, YUKIKO	
YAMAGATA, TAMIJI	

**ASSIGNEE-INFORMATION:**

NAME	COUNTRY
MITSUBISHI RAYON CO LTD	N/A
DAIWA KAGAKU KOGYO KK	N/A

APPL-NO: JP08334447  
APPL-DATE: December 2, 1996

INT-CL D01F006/46 , A47G027/02 , A61L009/01 , C08K005/24 , C08L023/12 ,  
(IPC): C08L101/12 , D02G001/00 , D02J001/22

**ABSTRACT:**

**PROBLEM TO BE SOLVED:** To produce a tobacco deodorant carpet excellent in resistance to washing by forming a crimped polyolefin-based fiber comprising a deodorant composed of a hydrazine derivative and an inorganic substance having adsorptivity.

**SOLUTION:** A deodorant composed of fine powder, obtained by mixing a hydrazine derivative such as a long-chain aliphatic mono- or dicarboxylic acid hydrazide or an aromatic mono- or dicarboxylic acid hydrazide having  $\leq 5\text{g/l}$  solubility in water at  $25^{\circ}\text{C}$ , preferably dodecanedioic acid dihydrazide with an inorganic substance having the adsorptivity, preferably a complex of silicon oxide with zinc oxide and alumina and having  $\leq 20\mu\text{m}$  average particle diameter is prepared. A polypropylene having 10-50g/10min melt flow rate is then compounded with 1-10wt.% resultant deodorant and the obtained composition is melt spun, drawn at 2-7 times draw ratio and heat-treated at  $\leq 20\%$  relaxation ratio with hot air at  $110\text{-}150^{\circ}\text{C}$  to afford a crimped tobacco deodorant polypropylene fiber having  $\geq 6\text{cm}^3/\text{g}$  bulkiness and  $>60\%$  deodorization ratio for ammonia and acetaldehyde.

COPYRIGHT: (C)1998,JPO

**BEST AVAILABLE COPY**